



## PRODUCT DATA

# 573.12

## BUTYL TAPE

### DESCRIPTION:

573.12 is a general purpose, butyl rubber based adhesive/sealing compound. It is produced in convenient ready-to-use tapes or beads. It adheres instantly and adhesion will increase over time. 573.12 is designed to yield a 100% cohesive failure on most substrates and in most conditions. This material is resilient yet pliable and easily worked by hand. 573.12 will not flow, sag or pump from joints due to thermal expansion or contraction. It will bond to:

- Polyethylene (HDPE)
- Polyester (Mylar™)
- Polyvinyl chloride (PVC)
- Glass
- Wood
- Aluminum
- Steel

Because of its excellent adhesion to most substrates, resistance to chemical attack, resiliency, creep resistance and its clean working properties, 573.12 may be used in almost any sealing application or as a laminating adhesive when applied as a 1/32-inch thick tape. The following examples are typical of the wide range of possible applications.

- Laminating adhesive for PVC, HDPE, joint compound, dry wall, concrete and laminates such as Formica®.
- Windows, panels and mullions in curtain wall and commercial building construction.
- A joint sealant metal frames and lap joints.
- Can be used wherever a freeze thaw material is required in refrigeration.

Surfaces where 573.12 is applied need not be completely clean, although they should be dry. Materials should be tested in the intended application for product suitability. 573.12 is chemically inert. It is non-corrosive to paint, metal, aluminum or plastic and will not swell rubber.

### PROPERTIES:

Property	Test Method	Typical Values
Color	ASTM D1729	Gray
Odor		None. Will not contaminate sweet butter.
Service Temperature		-40°F to 215°F
Cone Penetration, 300 g	ASTM D217	75 – 90 dmm
% Solids	ASTM C771	> 99% by weight
Specific Gravity	ASTM D297	1.64 ± 0.05 g/cm <sup>3</sup>
Weight per Gallon		13.7 ± 0.5 pounds per gallon
Tensile Yield	ASTM C907	20 – 25 psi
Migration	ASTM C772	Pass. No migration, contact stain only.
Elongation	ASTM C907	600%
Freeze-Thaw Stability	100,000+ cycles of 6-min @ -10°F + 2-min @ 80°F	Pass

## REGULATIONS and SPECIFICATIONS:

AAMA: Meets 802.3, Type II and 804.3 requirements.

### **deVan Sealants, Inc.**

6301 Prescott Avenue · P.O. Box 470375

St. Louis, MO 63147

(314) 383-1941 · Fax (314) 383-6491

[www.devansealants.com](http://www.devansealants.com)

#### CONDITIONS OF SALE AND LIMITATIONS OF WARRANTIES:

All deVan Sealants, Inc. products and materials are sold subject to the terms and conditions set forth in the technical data sheet, invoice, order acknowledgement and/or bill of lading. All statements, technical information and recommendations regarding such products are based on tests and examinations believed to be reliable but deVan Sealants, Inc. neither guarantees nor warrants their accuracy or completeness.

It shall be the sole responsibility of the user to determine the suitability of the deVan Sealants, Inc. product or material for each intended use and the user shall assume all risks and liability in connection with the use, or inability to use, the product or material.

To the exclusion of all other remedies, deVan Sealants, Inc. warrants and agrees to replace or, as its sole option, to refund the purchase price of that portion of any material or product supplied by deVan Sealants, Inc. which is proven, upon inspection within thirty (30) days of the date of receipt of such product or material, to be defective in material or workmanship. No salesperson, agent, employee or representative of deVan Sealants, Inc. has any authority to enlarge or change the terms of the warranty.

In no event shall deVan Sealants, Inc. be responsible for any special, indirect, consequential or incidental damages or loss including, without limitations, loss of profits or revenues, economic losses or loss of use, whether statutory or based on theories of contract or tort. THERE ARE NO OTHER AGREEMENTS, UNDERSTANDINGS, REPRESENTATIONS OR WARRANTIES, EXPRESS OR IMPLIED (INCLUDING ANY REGARDING MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE) NOT SPECIFIED HEREIN.

2015-05-05