



Sealants, Inc.

PRODUCT DATA

275.12

NON-SKINNING, STANDING SEAM PUMPABLE BUTYL CAULK

DESCRIPTION

275.12 is a premium quality, non-skinning, non-hardening, pumpable, butyl-based sealing caulk. It is formulated for sealing metal wall panels, standing roof seams, roof deck panels and expansion joints of similar and dissimilar materials without the need for a primer. It can be used in concealed joints in metal to metal assemblies. It is designed to be factory or field applied and is excellent for sealing joints against infiltration of air, dust, water and pollutants.

275.12 has excellent weathering properties and remains permanently elastic. It is flexible at low temperatures and will not dry out or crack on aging. It yields a 100% cohesive failure to most clean substrates when the bond is broken.

275.12 can be dispensed from a positive displacement pump (Graco 40:1 Bull Dog Pump or equivalent) or a manual applicator. The material cuts off easily at the nozzle and is not stringy. After application, the material develops a light film but remains soft and tacky so as to allow a good bond when two panels are butted together. Because it has residual tack, the sealant can create a bond between two panels up to six months after initial application.

PROPERTIES

Table with 3 columns: Property, Test Method, Typical Values. Rows include Color, Odor, Service Temperature, % Solids, % Shrinkage, Specific Gravity, Weight per Gallon, Flexibility, % Elongation, Slump, Viscosity, Extrudability, Freeze-Thaw Stability, and Weatherability.

Property	Test Method	Typical Values
Discoloration from Ultraviolet Light Exposure	ASTM D1148, 2000-hrs UVA-340	No change.
High Temperature Aging	1-year @ 180°F	No sagging, cracking or property loss.
Tack-free Time	ASTM C679	Relatively tack-free after 18-hours.
Engageability	TP-002 Age 7-days @ 158°F + 14-days @ 77°F	The sealant will bond to another metal substrate and form a web with cohesive failure when pulled apart.
Staining	ASTM D925, Method A	No staining of the painted metal.
	ASTM D925, Method B	No migration stain, flow or skinning.
Corrosive Effects	TP-008	No evidence of pitting or corrosion of aluminum or galvanized steel after 7-days aging of the sealant on metal in water @ 158°F.
Bubble Formation	TP-004	<25% of surface after 120-hours @ 158°F.
Shelf Life		2-years when stored in the original container at normal warehouse temperatures.

## **REGULATIONS and SPECIFICATIONS**

Department of Defense: Meets UFC 3-110-03, Section 5-3.3.3 Seam Sealant requirements.

Federal Specification: TT-C-1796A, Type I, Class A.

LEED: Conforms to Leadership in Energy and Environmental Design 2009 for New Construction, Indoor Environmental Quality: Section 4.1, Low-Emitting Materials: Adhesive & Sealants (SCAQMD) Rule # 1168, VOC limits.

NAAMM: Meets standard SS-1a-68.

U.S.D.A.: Is acceptable to the U.S. Department of Agriculture for use in meat and poultry processing area under federal inspection.

### **deVan Sealants, Inc.**

6301 Prescott Avenue · P.O. Box 470375

St. Louis, MO 63147

(314) 383-1941 · Fax (314) 383-6491

[www.devansealants.com](http://www.devansealants.com)

#### **CONDITIONS OF SALE AND LIMITATIONS OF WARRANTIES:**

All deVan Sealants, Inc. products and materials are sold subject to the terms and conditions set forth in the technical data sheet, invoice, order acknowledgement and/or bill of lading. All statements, technical information and recommendations regarding such products are based on tests and examinations believed to be reliable but deVan Sealants, Inc. neither guarantees nor warrants their accuracy or completeness.

It shall be the sole responsibility of the user to determine the suitability of the deVan Sealants, Inc. product or material for each intended use and the user shall assume all risks and liability in connection with the use, or inability to use, the product or material.

To the exclusion of all other remedies, deVan Sealants, Inc. warrants and agrees to replace or, as its sole option, to refund the purchase price of that portion of any material or product supplied by deVan Sealants, Inc. which is proven, upon inspection within thirty (30) days of the date of receipt of such product or material, to be defective in material or workmanship. No salesperson, agent, employee or representative of deVan Sealants, Inc. has any authority to enlarge or change the terms of the warranty.

In no event shall deVan Sealants, Inc. be responsible for any special, indirect, consequential or incidental damages or loss including, without limitations, loss of profits or revenues, economic losses or loss of use, whether statutory or based on theories of contract or tort. THERE ARE NO OTHER AGREEMENTS, UNDERSTANDINGS, REPRESENTATIONS OR WARRANTIES, EXPRESS OR IMPLIED (INCLUDING ANY REGARDING MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE) NOT SPECIFIED HEREIN.

2016-09-02