



Sealants, Inc.

PRODUCT DATA

535.2

BUTYL SEALANT FOR PRE-ENGINEERED METAL BUILDINGS AND RV ASSEMBLY

DESCRIPTION:

535.2 is formulated with high performance butyl elastomer for pre-engineered metal building assembly and RV manufacturing industries. It is soft, resilient and easily worked by hand and adheres to almost any normal commercial surface without being cleaned. 535.2 has excellent weathering characteristics while retaining adhesion and elasticity in both hot and cold environments. It is designed to seal exposed joints against infiltration of air, dust, water and pollutants.

PROPERTIES:

Property	Test Method	Typical Values
Color	ASTM D1729	Natural (off-white)
Odor		None
Service Temperature		-40°F to 200°F
Cone Penetration, 300 g	ASTM D217	85 – 100 dmm
% Solids	ASTM C771	> 99% by weight
Specific Gravity	ASTM D297	1.86 ± 0.05 g/cm ³
Weight per Gallon		15.5 ± 0.5 pounds per gallon
Tensile Yield	ASTM C907	16 psi
Flexibility	ASTM C765	Passes 1-inch mandrel bend at -10°F
Staining	ASTM D925, Method A – 7-days @ 70°C (158°F)	No contact stain
	ASTM D925, Method B – 1000-hours UVA-340 exposure @ 60°C (140°F)	No migration stain or breakdown.
Weatherability	ASTM D750	No apparent change of physical properties after 1000-hours QUV exposure. No bleed-out or discoloration.
Shelf Life		Minimum 1-year when stored in the original container at normal warehouse temperatures.

REGULATIONS and SPECIFICATIONS:

Federal Specification: TT-C-1796A, Type II, Class B

LEED: Conforms to Leadership in Energy and Environmental Design 2009 for New Construction, Indoor Environmental Quality: Section 4.1, Low-Emitting Materials: Adhesive & Sealants (SCAQMD) Rule # 1168, VOC limits.

deVan Sealants, Inc.

6301 Prescott Avenue · P.O. Box 470375
St. Louis, MO 63147
(314) 383-1941 · Fax (314) 383-6491
www.devansealants.com

CONDITIONS OF SALE AND LIMITATIONS OF WARRANTIES:

All deVan Sealants, Inc. products and materials are sold subject to the terms and conditions set forth in the technical data sheet, invoice, order acknowledgement and/or bill of lading. All statements, technical information and recommendations regarding such products are based on tests and examinations believed to be reliable but deVan Sealants, Inc. neither guarantees nor warrants their accuracy or completeness.

It shall be the sole responsibility of the user to determine the suitability of the deVan Sealants, Inc. product or material for each intended use and the user shall assume all risks and liability in connection with the use, or inability to use, the product or material.

To the exclusion of all other remedies, deVan Sealants, Inc. warrants and agrees to replace or, as its sole option, to refund the purchase price of that portion of any material or product supplied by deVan Sealants, Inc. which is proven, upon inspection within thirty (30) days of the date of receipt of such product or material, to be defective in material or workmanship. No salesperson, agent, employee or representative of deVan Sealants, Inc. has any authority to enlarge or change the terms of the warranty.

In no event shall deVan Sealants, Inc. be responsible for any special, indirect, consequential or incidental damages or loss including, without limitations, loss of profits or revenues, economic losses or loss of use, whether statutory or based on theories of contract or tort. THERE ARE NO OTHER AGREEMENTS, UNDERSTANDINGS, REPRESENTATIONS OR WARRANTIES, EXPRESS OR IMPLIED (INCLUDING ANY REGARDING MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE) NOT SPECIFIED HEREIN.

2016-03-10